Valid from: 04.10.24
Revision: 3

Product: DensM® 175 [WNiFe]

Manufacturing: powder metallurgy (mixing, pressing, sintering), heat treatment and mechanical processing.
Material properties are measured at room temperature on separate test samples.

1. Chemical composition

Element	Range (Min. – Max.)	Typical value
Tungsten	92.5 – 93.0 %	92.7 %
Binder (Ni+Fe)	7.0 – 7.5 %	7.3 %

2. Mechanical and Physical Properties

Property	Range (Min. – Max.)	Typical value
Tensile strength [Mpa]	760 – 980	910
Fracture elongation [%]	5 - 30	20
Modulus of elasticity [Gpa]	340 – 360	350
Hardness [HV10]	300 – 330	310
Density [g/cm3]	17.3 – 17.7	17.5
Thermal conductivity [W/mK]	107 – 113	110
Coefficient of thermal expansion. [1/C]	5.6 – 5.8 x 10-6	5.7 x 10-6

3. Metallography

The microstructure consists of two phases: a tungsten-rich phase (spherical phase) and a NiFe-rich phase (binder). Both phases are homogeneously distributed, as can be clearly seen in the photo. The particle size of the spherical tungsten-rich phase is ideally between 10 and 70 µm, which ensures optimal material properties.



4. Applications

Material for tool holders and high-speed spindles
Material for radiation shielding (e.g. in medical diagnostics and radiation therapy)
Material for mass balancing in rotating systems (avionics, radar, crankshafts, etc.)
Casting Molds for die casting of aluminium, magnesium, zinc and copper
Tools for hot forging

5. Standards and certificates

Our DensM® products fully comply with the ASTM B777 standard.
Upon request, we are pleased to provide factory certificates in compliance with EN 10204, available as either a 2.2 or 3.1 inspection certificate.

6. Delivery program

Rods (in stock), bars, plates, and finished parts according to technical drawings

© Copyright Molytun GmbH | All rights reserved

Molytun GmbH
Gaußstr. 10, 85757 Karlsfeld
Phone: +49 (0) 8131 3102054
info@molytun.com, www.molytun.com